

ACRYLIC CLEAR

Flexible Clear Coating

Form: Aerosol

Color: Not determined

Odor: Solvent

pH: N/A

Solubility (in water): Not determined
(in mineral spirits): Not determined

VOC Content (% by weight): 61.2

Flash Point (ASTM D-7821): -2°F

Specific Gravity: 0.77-0.85 g/ml

Density: 6.43-7.09 lb/gal

Storage Stability (at 70°F): 1 year

| <u>Ingredients</u> | <u>C.A.S. #</u> |
|--------------------|-----------------|
| Acetone | 67-64-1 |
| Propane | 74-98-6 |
| Toluene | 108-88-3 |
| n-butane..... | 106-97-8 |
| VM&P Naphtha | 64742-89-8 |

| Other Uses... |
|-------------------------------------|
| • Battery Protector |
| • Street Sign Coating |
| • Athletic Equipment Coating |
| • Graffiti Preventative |
| • Decorative Metal Protector |
| • Auto Lettering Protector |
| • Document Laminating |
| • Waterproofing |

Directions: Surface must be free of dirt, moisture, grease, loose rust and paint. Shake can vigorously for one minute after agitator begins to rattle, and shake often during use. Hold nozzle 10 to 12 inches from surface and apply by spraying in quick, short bursts. Apply several thin coats rather than a single heavy coat. For best results, use when temperature is above 65°F and humidity below 85 percent. After use, clear the nozzle by turning can upside down and pressing valve for 1 to 2 seconds.

| HMIS® | | | NFPA® | | |
|---------------------------|----------|---|---------------|---------------------------|------|
| | Severe | 4 | Extreme | | |
| Health | Serious | 3 | High | Health | 2 |
| Flammability | Moderate | 2 | Moderate | Flammability | 4 |
| Reactivity | Slight | 1 | Slight | Reactivity | 0 |
| Personal Protection | Minimal | 0 | Insignificant | Special Precautions | None |